

CHIMERA S4 SRC



DESCRIERE	NORMA EN ISO 20345:2011	RESULTAT CERINTE NORMA	
Fete: PVC -8% cauciuc nitrilic	5.4.2 Grosime 5.4.4 Rezistentă la alungire 5.4.5 Rezistentă la flexare	3.1 mm 1.8 N/mm ² 296% Fara crapare inainte de 150.000 flexari	≥ 1.00 mm 1.3 to 4.6N/mm ² ≥ 250% Fara crapare inainte de 150.000 flexari
Bombeau de siguranta: Otel	5.3.2.3 Rezistentă la impact 5.3.2.4 Rezistentă la compresiune	17.5 mm 15 mm	≥ 14 mm ≥ 14 mm
Talpa: PVC -8% cauciuc nitrilic	5.8.2 Rezistentă la sfasiere 5.8.3 Rezistentă la abraziune 5.8.4 Rezistentă la flexare 5.8.5 Hidroliza 6.2.2.2 Atistatic 6.4.2 Rezistentă la uleiuri 5.11 Rezistentă la alunecare pe placi ceramice spalate cu detergent Alunecare pe suprafata totala a talpii	11.6 kN/m 159 mm ³ 2.5 mm 2.5 mm Uscat: 1,05 x10 ⁸ Ω Umed: 7,36 x10 ⁷ Ω 9% 0,64	≥ 8 kN/m ≤ 250mm ³ ≤ 4,0 mm ≤ 6,0 mm ≤ 12% ≥ 0,32

	Alunecare pe calcai	0,44	$\geq 0,28$
	Rezistenta la alunecare pe placi din otel acoperite cu glicerina		
	Alunecare pe suprafata totala a talpii	0,18	$\geq 0,18$
	Alunecare pe calcai	0,13	$\geq 0,13$
	6.2.4 Absorbtia de energie in zona calcaiului	28 J	$>20 J$

MARIMI : 36-48

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39
0733 897519 C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207
www.exena.it – info@exena.it - pec: amministrazione@pec.exena.it

CHIMERA S4 SRC



DESCRIPTION	NORM EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER:			
PVC – 8% Nitrilic rubber	5.4.2 Thickness	3,10 mm	≥1,00 mm
	5.4.4 Modulus at 100 % elongation:	1,8 N/mm ²	1,3 to 4,6N/mm ²
	5.4.5 Flexing resistance:	296%	≥ 250%
		no cracking before 150.000 flexes.	no cracking before 150.000 flexes.
SAFETY TOE CAP:	5.3.2.3 Impact resistance	17,5 mm	≥14 mm
Steel	5.3.2.4 Compression resistance	15 mm	≥ 14 mm
SOLE:	5.8.2 Tear strength	11,6 kN/m	≥ 8 kN/m
PVC – 8% Nitrilic rubber	5.8.3 Abrasion resistance	159 mm ³	≤ 250 mm ³
	5.8.4 Flexing resistance	2,5 mm	≤ 4,0 mm
	5.8.5 Hydrolysis	2,5 mm	≤ 6,0 mm
	6.2.2.2 Antistatic	secco: 1,05 x10 ⁸ Ω	tra 1,00x10 ⁵ Ω
		umido: 7,36 x10 ⁷ Ω	e 1,00x10 ⁹ Ω
	Oils resistance	9 %	≤ 12%
	5.11 Pressed ceramic tile floor on detergent resistance		
	Flat slip	0,64	≥ 0,32
	Heel slip	0,44	≥ 0,28
	Stainless steel plate on glycerin resistance		
	Flat slip	0,18	≥ 0,18
	Heel slip	0,13	≥ 0,13
	6.2.4 Energy absorption of seat region:	28 J	>20 J

SIZES: 36-48

Traducere din limba engleza - in conformitate cu documentul

EXENA

DECLARATIE DE CONFORMITATE UE

M22 -Vers. 00

Conform regulamentului (UE) 2016/425 – Anexa IX, **Exena srl** DECLARA
ca echipamentul individual de protectie si lotul respectiv de productie
descrie mai jos:

Articol: **CHIMERA**



Este in conformitate cu standardul: EN ISO 20345:2011

Clasa: II

Categoria de marcaj: S4 SRC

Nr. certificat: F-130-05593-22

Data: 06.10.2022

EMIS DE: CIMAC – 0465

Civitanova Marche,

Aplicata parafa firmei EXENA S.R.L.

Sediul in Via Breda, 7/A

Civitanova Marche (MC), ITALIA ,

Sfârșitul traducerii

DECLARATION OF CONFORMITY UE

M22 - Ver.00

As per Regulation (UE) 2016/425 - Annex IX, Exena Srl declares that the ppe and the relative production batch below described:

item:

CHIMERA

batch:



conforms to the standard:

EN ISO 20345:2011

class:

II

marking category:

S4 SRC

certificate numb.:

F-130-05593-22

date:

06/10/2022

issued by:

CIMAC - 0465

Civitanova Marche

EXENA S.r.l.
Via Breda, 7 - Z.na Ind. A
Tel. 0733 897256 Fax 0733 897519
P. IVA 01336080435 - MC
CEO

EXENA S.r.l.

Via Breda, 7 - Z.na Ind. A 62012 - CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

P. IVA: 01336080435 - Reg. Impr. Trib. MC N. 21676/1998 - CCIAA MC 22988

www.exena.it - info@exena.it - pec: amministrazione@pec.exena.it