




NITRILE- CHEM 41-200



CHARACTERISTICS

- Glove with full nitrile coating
- Flocked cotton backing
- The cotton flock lining optimizes wearing comfort
- Chlorinated finish
- Suitable for work in wet working conditions
- Anti-slip profile for better grip
- Very flexible glove that protects the hand and forearm against various chemicals
- Suitable for contact with many foodstuffs
- Length: 330 mm
- Thickness: 0.40 mm

Article number: 1.41.200.00

SUITABLE FOR ACTIVITIES IN E.G.

- Petrochemistry
- Industry
- Transport & Logistics
- Cleaning services
- Shipping
- Agri

COLOUR

Green

SIZES

7/S to 11/XL

PACKAGING

- 1 pair per polybag
- 12 pair per bundle
- 144 pair per outer carton

EN 388:2016
+A1:2018



EN ISO 374-1:2016
+A1:2018/Type A



EN ISO 374-5:
2016



CE 0598
EN ISO 21420:2020

PRODUCT INFORMATION

SIZE	ARTICLE NO.	EAN-CODE 1 PAIR (POLYBAG)	EAN-CODE 12 PAIR (BUNDLE)	EAN-CODE 144 PAIR (OUTER CARTON)
7/S	1.41.200.07	'8718249007231	'8718249007248	'8718249007255
8/M	1.41.200.08	8718249007262	8718249007279	8718249007286
9/L	1.41.200.09	8718249007293	8718249007309	8718249007316
10/XL	1.41.200.10	8718249007323	8718249007330	8718249007347
11/XXL	1.41.200.11	8718249007354	8718249007361	8718249007378

EXPLANATION OF ICONS

EN388:2016+A1:2018



4101X

EN388:2016+A1:2018



abcdef

Bescherming tegen mechanische risico's

A = Abrasion resistance (0-4)
B = Cut resistance (0-5)
C = Tear resistance (0-4)
D = Puncture resistance (0-4)
E = Cut resistance (according to EN ISO 13977 (A to F))
F = Impact protection (optional) (P = Passed)

Note: X = not tested or not applicable

STORAGE INSTRUCTIONS

The gloves should be stored in a clean, cool and dry place and not compressed in the original packaging. Do not expose the gloves to direct sunlight. Please ensure that the packaging and gloves are not damaged during shipping.

TEST INSTITUTE

These gloves are certified by: SATRA Technology Europe Ltd (Notified Body no. 2777), Bracetown Business Park, Clonree, Dublin D15 YN2P, Ireland.

Protection against chemicals and microorganisms

EN ISO 374-1:2016/Type A		
	Chemical	EN 15523:2015 permeation level
EN ISO 374-1:2016 /Type A AJKLMNPT	Methanol (A)	2
	n-Heptane (J)	6
	40% Sodium Hydroxide (K)	6
	96% Sulphuric Acid (L)	3
	65% Nitric acid (M)	2
	99% Acetic acid (N)	3
	25% Ammonium hydroxide (O)	6
	30% Hydrogen peroxide (P)	6
	37% Formaldehyde (T)	6

EN ISO 374-4:2019	
Cas number	Class
(A) 67-56-1	Primary alcohol
(J) 142-82-5	Saturated hydrocarbon
(K) 1310-73-2	Inorganic base
(L) 7664-93-9	Inorganic mineral acid, oxidizing
(M) 7697-37-2	Inorganic mineral acid, oxidizing
(N) 64-19-7	Organic acid
(O) 1336-21-6	Organic base
(P) 7722-84-1	Peroxide
(S) 7664-39-3	Inorganic mineral acid
(T) 50-00-0	Aldehyde

Resistance to Bacteria & Fungi and Virus

Chemical	Average degredation %
Methanol (A)	70.1%
n-Heptane (J)	0.0%
40% Sodium Hydroxide (K)	4.5%
96% Sulphuric Acid (L)	61.9%
65% Nitric acid (M)	98.7%
99% Acetic acid (N)	91.9%
25% Ammonium hydroxide (O)	-5.8%
30% Hydrogen peroxide (P)	-11.7%
37% Formaldehyde (T)	15.6%

EN ISO 374-5:2016		
EN ISO 374-5:2016	Resistentie tegen bacteriën & schimmels	Resistentie tegen Virus
 VIRUS	PASS	PASS

EN ISO 374-2:2014	
Air leak test - Pass	Water leak test - Pass

EN ISO 374-1:2016 Permeation levels are based on the following lead times:

Performance level	1	2	3	4	5	6
Minimum lead times (in min.)	>10	>30	>60	>120	>240	>480

DECLARATION OF CONFORMITY

For a copy of the declaration of conformity, we refer you to the following link: www.oxxa.work/doc

YOUR SUPPLIER