



DEXTERITY




POWDER
FREE



CHEMICAL
RESISTANT

NITRI-FIT 44-526



CHARACTERISTICS

- Unpowdered non-sterile disposable nitrile glove
- Relief on the fingertips
- Smooth interior
- Extremely easy to slip on due to the rolled cuff
- Ambidextrous design
- 100% latex-free to accommodate users with a latex allergy
- Thickness: cuff 0,05 mm / palm 0,07 mm / fingers 0,08 mm
- Length: 240 mm
- Weight: 3,5 grams (+/- 0,3 grams)
- AQL 2,5 (EN 374)
- Suitable for contact with many types of food products
- Packaged per 100 units in a dispenser

Article number: 1.44.526.00

SUITABLE FOR ACTIVITIES IN E.G.

- Food industry
- Agriculture
- Hospitality
- Maintenance
- Laboratories
- Automotive

COLOUR

Blue

SIZES

7/S to 10/XL incl.

PACKAGING

- 100 units per dispenser
- 10 dispensers in outer box

EN ISO 374-1:2016
+A1:2018/Type B



KPT

EN ISO 374-5:
2016




VIRUS



CE 2777
EN 420:2003+A1:2009

PRODUCT INFORMATION

SIZE	ARTICLE NO.	EAN CODE 100 UNITS (DISPENSER)	EAN CODE 10 DISPENSERS (OUTER BOX)
7/S	1.44.526.07	8718249068232	8718249068270
8/M	1.44.526.08	8718249068201	8718249068249
9/L	1.44.526.09	8718249068218	8718249068256
10/XL	1.44.526.10	8718249068225	8718249068263



CLARIFICATION OF PICTOGRAMS

Protection against chemicals and microorganisms

EN ISO 374-1:2016/Type B		
EN ISO 374-1:2016 /Type A	Chemicals	EN 16523:2015 permeation level
	40% Sodium Hydroxide (K) 30% Hydrogen peroxide (P) 37% Formaldehyde (T)	6 4 6

EN ISO 374-4:2019	
Cas number (K) 1310-73-2 (P) 7722-84-1 (T) 50-00-0	Class Inorganic base Peroxide Aldehyde
Chemicals	Average degradation %
40% Sodium Hydroxide (K) 30% Hydrogen peroxide (P) 37% Formaldehyde (T)	-3.9% 8.1% 2.9%

Resistant against bacteria, mould and viruses

EN ISO 374-5:2016		
EN ISO 374-2:2014	Resistance against bacteria and mould	Resistance against viruses
	PASS	PASS

EN ISO 374-2:2014	
Air leak test - Pass	Water leak test - Pass

EN ISO 374-1:2016 Permeation levels are based on the following breakthrough times:

Performance level	1	2	3	4	5	6
Minimal breakthrough times (in min.)	>10	>30	>60	>120	>240	>480

STORAGE CONDITIONS

The gloves should be kept in a clean, cool and dry place and not kept compressed in their original packaging. Do not expose the gloves to direct sunlight. Make sure that the packaging and the gloves are not damaged during shipping.

TESTING INSTITUTE

These gloves are certified by: SATRA Technology Europe Ltd (Notified Body no. 2777), Bracetown Business Park, Cloness, Dublin D15 YN2P, Ireland.

DECLARATION OF CONFORMITY

For a copy of the declaration of conformity, we refer you to the following link: www.oxxa-safety.com/doc

YOUR SUPPLIER: