

Technical Data Sheet

Sontara® Aerospace Grade Pop-Up
 50.4% Woodpulp – 49.6% PET
 Creped Smooth Embossed
 White

TYPICAL MATERIAL PROPERTIES

TEST	ORIENTATION	UNITS	TARGETS	METHODS
Basis Weight		g/m ²	73	WSP 130.1
Thickness		mm	0.53	WSP 120.6
Absorption Capacity		%	555	WSP 10.1
Extrinsic absorption capacity		ml/m ²	410	WSP 10.2
Grab Tensile Strength	MD	N/4in	136	ASTM D5034
	CD	N/4in	73	ASTM D5034
Strip Tensile Strength	MD	N/5cm	140	WSP 110.4
	CD	N/5cm	53	WSP 110.4

WSP = Worldwide Strategic Partners: Standard Test Methods for the Nonwoven Industry

Glatfelter Sontara Asturias S.A.U